

## BAYBLOCK<sup>®</sup> QS

### Characterization

Bayblock QS coating is a technologically advanced, high-solids, fire resistant, thixotropic, acrylic elastomeric quick set coating.

### Properties / Applications

Bayblock QS coating is formulated for the protection of sprayed-in-place polyurethane foam, stucco, cinder blocks, metal, single ply, and with appropriate base coats, asphaltic and modified bituminous roofing. Bayblock QS coating provides an excellent protective membrane that remains flexible even under adverse conditions. As with any product, use of Bayblock QS coating must be tested (including, but not limited to, field testing) in advance by the user to determine suitability.

### General Application Instructions

Bayblock QS coating may be applied by medium nap rollers, brushes or by conventional or airless spray equipment. Airless spray application is the most efficient form of application. Rolling or brushing may be used for touchup, flashing and edge terminations or to fill voids, pinholes, holidays or cracks. Contact Bayseal technical service personnel for specific recommendations, pricing, and availability of spray and auxiliary equipment.

Apply Bayblock QS coating only to clean, dry, sound surfaces that are free of loose particles or other foreign matter. A primer may be required subject to the type and/or condition of the substrate. Consult Bayseal technical service personnel for specific primer recommendations and substrate preparation procedures. Apply only to roofs that have adequate positive drainage (i.e. a minimum slope of 1/8 inch per foot).

The contents of each container should be thoroughly power mixed for ten (10) to fifteen (15) minutes before application. Thinning is not recommended. It is recommended that Bayblock QS coating be sprayed in multiple coats applied in multidirectional (north-south, east-west) passes to insure uniform film build and to avoid pinholing. Backrolling sprayed material may be necessary to fill pinholes in substrate. Final cured dry film thickness must be free of voids, cracks or blisters. Coating application should be suspended immediately and Bayseal technical service personnel contacted if the results obtained are less than desirable.

Apply three (3) or more coats of Bayblock QS coating at the rate of 1 - 1.25 gallons per 100 square feet per coat. As a visual aid in the application of multiple coats, alternate coats may be tinted a light to medium gray. Tinting may be necessary during application at temperatures between 50°F and 70°F to accelerate the curing process. Minimum dry film thickness shall be 25 mils.

Accentuated surface profiles, which increase total surface area, will require a proportionate increase in the amount of Bayblock QS coating needed to satisfy specified minimum dry mil thickness. If required, roofing granules may be broadcast into coating application at the rate of 35-40 pounds per 100

# BAYBLOCK<sup>®</sup> QS

square feet. No foot traffic shall be permitted on the coated surface for 72 hours after application.

## Dry Physical Properties\*

Properties	Test Method	Value at 73°F
Tensile Strength	ASTM D 412	188 psi
Elongation	ASTM D 412	169 %
Impact Resistance	ASTM D 2794	Exceeds 160 in/lb
Hardness, Shore A	ASTM D 2240	45
Fire Rating	UL 790 Class A	Combustible Deck Class B
Dirt Pickup	% Resistance	99
Solids by Weight	ASTM D 6083	70 ± 2%
Solids by Volume	ASTM D 6083	55 ± 1%
Theoretical Coverage DFT		100 s.f./gal at 9.5 dry mils
Density		12 lbs/gal
Temperature Limits		-30°F to 200°F
Color	Topcoat	White, Gray
	Basecoat	Gray

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

## Wet Physical Characteristics

Property	Value
Flash Point (ASTM D 93)	No flash to boiling
Shelf Life	12 months when properly stored
Clean Up	Water
Thinner	Not Recommended

## Product Reactivity & Application\*

Property	Value
Dry to Touch	4 hours
Tack Free time	12 hours
Recoat	12 - 24 hours

Note: Adhesion should not be tested within one hour of application.

## **BAYBLOCK<sup>®</sup> QS**

### **Limitations and Precautions**

Bayblock QS is a water-based elastomeric acrylic coating which will freeze and become unusable at temperatures below 32°F. Protect from freezing during shipment and storage. Do not store material at temperatures below 50°F. Do not apply Bayblock QS coating when ambient air and substrate temperatures fall below 50°F or when there is a possibility of temperature dropping below 32°F within a 24-hour period after application.

Fresh galvanized steel requires a primer or surface treatment prior to coating with Bayblock QS coating. Please contact Bayseal technical personnel for specific primer recommendations.

Do not apply over wet substrates or when inclement weather is imminent. Total cure of Bayblock QS coating requires complete evaporation of water. Cool temperatures and high humidity retard cure. Furthermore, all white or light colored coatings can cause a premature artificial dew zone during the curing process under certain climatic conditions.

This is generated as the water in the coating evaporates, cooling the white surface and attracting moisture in the form of dew. Therefore, do not apply if climatic conditions prevent complete cure before rain, dew or freezing temperatures.

Bayblock QS coating is not a vapor barrier coating and is not recommended for use over most cold storage installations. Where a vapor barrier is required, contact Bayseal technical service personnel for proper selection and installation procedures.

---

### **Health and Safety Information**

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling this product. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., safety data sheets and product labels. For further information contact your Bayseal representative.

---

## BAYBLOCK<sup>®</sup> QS

---

**DISCLAIMER:** To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Bayseal to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Bayseal. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY BAYSEAL EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.”

The information herein is to assist customers in determining whether our products are suitable for their applications. Customer assumes full responsibility for quality control, testing, and determination of suitability of product for its intended use or application. Accella warrants only that the material shall meet its specifications; this warranty is in lieu of all other written, expressed or implied warranties and Accella expressly disclaims any warranty of merchantability, fitness for a particular purpose, or freedom from patent infringement. Accordingly, buyer assumes all risks whatsoever as to the use of the material. Buyer's exclusive remedy as to any breach of warranty, negligence or other claim shall be limited to the purchase price of the material. Failure to adhere to any recommended procedures shall relieve Accella of all liability with respect to the material or the use thereof.

---

Accella Polyurethane Systems  
2400 Spring Stuebner Rd  
Spring, TX 77389  
United States  
1-844-922-2355

